Pink Recloseable Bag







Features

- · Our pink antistatic bags are blow-molded with anti static additives from LDPE and LLDPE
- · Soft texture and flexible
- Surface resistance of 108-1011Ω
- · Static release time is >2 secs

Pink anti static bags have the ability to dissipate a static charge to ground preventing static chargebuilding up on the package or device. The material is also antistatic and will not charge up when rubbed against other materials.

Please note these bags have no shielding ability. A static field or discharge occurring outside the bag will penetrate the bag and damage electronics inside.

Additional Notes:

We recommend that all of our pink anti static bags be used within 2 years from the date of manufacture. Store this product in its original packaging in a climate-controlled environment where temperature ranges from 21°C to 23°C and relative humidity is 45% to 50%.



Configuration(s):

Bags are offered with a bottom fold and two hot seals to each side.

PINK ANTISTATIC BAG ANTISTAT REORDER CODE ANTOO3 PAB



Standard Bag Artwork:

Our pink antistatic bags are produced with the following sample artwork as standard. The bags come complete with artwork and write on panel.

Newark.com/multicomp-pro Farnell.com/multicomp-pro sg.element14.com/b/multicomp-pro



Pink Recloseable Bag



Test Conditions:

The following results were taken under the following environmental test conditions: Temperature: 22°C / Humidity: 46%

Technical Parameters

| Item | Test Standard | Result |
|--------------------------|----------------|--|
| Film Composition | N/A | LDPE |
| Film Thickness | Micron Meter | 75 micron (±8%) (where applicable) |
| Melt Index | GB3682 | 2.1 g/10min |
| Surface Resistivity | GB3682 | <10 ¹⁰ Ω/sq |
| Water Absorption Rate | GB/96-04-10 | 0.5% |
| Density | GB 1033 | 0.92 g/cm |
| Tensile Strength | GB/96-04-10 | MD: 32.01 MPa TD: 33.75 MPa |
| Breaking Elongation Rate | GB/96-04-10 | MD: 1200% TD: 685% |
| Friction Coefficient | GB/96-04-10 | Outer Surface: 0.09 Us Inner Surface: 0.08 Ud |
| Static Dissipation | SJ/T10694-1996 | <2 Secs |
| Appearance | GB/96-04-10 | Translucent Sheet (No powder and oil) |
| Size | GB/96-04-10 | Thickness: +10% Length: +3mm Width: +3mm |

Part Number Table

| Description | Part Number |
|---|-------------|
| Pink Recloseable Bag 300 Gauge / 75 Micron, 102mm × 152mm | MP-003-0002 |

Important Notice: This data sheet and its contents (the "Information") belong to the members of the AVNET group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Multicomp Pro is the registered trademark of Premier Farnell Limited 2019.

Newark.com/multicomp-pro Farnell.com/multicomp-pro sg.element14.com/b/multicomp-pro

