()ideal-tek

TECHNICAL DATA SHEET

Carbon steel type C

General notes:

- » Carbon style (material number 1.1221, Ck60, AISI 1060)
- » contains from 0,57-0,65 wt% carbon
- » magnetizable
- » will be hardened by heat treatment, max. hardness 57 HRC
- » poor resistance to corrosion
- » used where strength and/or hardness are of primary concern
- » typical applications include tweezers and cutting tools for the electronic industry, watch-makers, jewelers applications

Composition

Component	Wt.%	Component	Wt.%	Component	Wt.%
С	0.57-0.65	Si	0.15-0.35	Cr	≤0.4
Р	≤0.035	S	≤0.035		

Mechanical properties

Density	7.9 g/cm ³		
Hardness, Vickers	55-57 HRC		
Tensile strength, ultimate	850-1000 MPa		
0.2% Yield stress	500 MPa		
Modulus of elasticity	200 GPa		
Thermal properties			
Coef. of lin. therm expansion	11 E-6/°C	20°C-100°C	
Coef. of lin. therm expansion	12 E-6/°C	20°C-300°C	
Specific heat capacity	0.502 J/(g⋅K)		
Thermal conductivity	52 W/(m⋅K)		

Electrical properties

Resistivity

0.18 E-4 Ohm.cm

This document contains information based on average values as obtained from the results of laboratory tests and observations made on the material. Ideal-Tek SA declines all responsibility from an improper use of the product described in this document.

() ideal-tek

TECHNICAL DATA SHEET

Engineering coating type DN

General notes:

- » PVC FOAM
- » very soft and elastic, good tear resistance
- » very good abrasion/wear resistance (improved life-time)
- » good chemical resistance (oils, grease, fuels, acids, detergents and soaps, alcohols)
- » electrically static dissipative, ESD-safe material!
- » typical applications include ESD-safe handles, floor and work surface mats

Physical Properties

Metric

Density	
Water Absorption	

0.530 g/cc
2.86 %

Mechanical properties

56.7
7.60 MPa
0.317 MPa
171 %

Thermal properties

Maximum Service Temperature, Air	70 °C
Minimum Service Temperature, Air	-150 °C

Electrical properties

Surface Resistivity 10⁹-10¹⁰ Ohm

This document contains information based on average values as obtained from the results of laboratory tests and observations made on the material. Ideal-Tek SA declines all responsibility from an improper use of the product described in this document.

