

Einsatzempfehlung

Material	Stahl N/mm ²				Rostfreie Stähle		Guss		NE-Metalle			Superleg.		Stahl gehärtet	
Zugfestigkeit	<500	<800	<1200 (-<HRC38)	<1600 (-<HRC48)	<800	<1200	GG	GGG	Al Knetleg.	Al Si<10%	Cu,Ms	Ti/Ni/Co <900	900-1500	HRC 48-57	HRC 58-63
4000 867 989 - Vc (m/min)	23	12	8		8	8	20		28	24	16				
Kühlung	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl	Emulsion/Öl		Emulsion/Öl	Emulsion/Öl	Emulsion/Öl				