



EVO-PLAS TENSOL 70

2 COMPONENT CEMENT

KEY FEATURES

- Forms a glass clear bond
- Excellent weathering resistance
- Can be used to create either a lamination or butt joint for cast acrylic.

DESCRIPTION

Evo-Plas Tensol 70 is a two component acrylic cement that hardens at room temperature by polymerisation. It produces high strength bonds to acrylic sheet and offers excellent weathering resistance.

RECOMMENDED USE

Evo-Plas Tensol 70 is intended for cementing acrylic sheet to itself, but it will bond acrylic sheet to other materials such as wood. Applications include sign making, model making, structural engineering and acrylic sheet repair. Unsupported gaps of up to 1mm can be produced.

Evo-Plas Tensol 70 may also be used to bond extruded acrylic sheet but, will cause surface crazing and stress cracking of the sheet unless the sheet is annealed prior to bonding.

Evo-Plas Tensol 70 is not recommended for structural applications on aircraft.

The bonds obtained using **Evo-Plas Tensol 70** are of approximately the same strength as the acrylic sheet, typical joint strengths are 35 MPa for a cold cured joint and 45 MPa for a post cure heat treated joint.

IMPORTANT

Before embarking on any work involving **Evo-Plas Tensol 70** the safety data sheets for **component A** and **component B** should be carefully studied by those carrying out the work.

METHOD OF USE

SURFACE PREPARATION

- Substrates to be bonded should be perfectly clean, dry and free from dust and grease, if necessary they can be cleaned with **Bostik Anti-static cleaner**, or **Bostik Cleaner 9**.

ADHESIVE PREPARATION

- Evo-Plas 70 Component A** must be at room temperature i.e. 16 - 20°C. If it has been stored below 15°C it must be allowed to come to room temperature before use. This could take several hours.

MIXING RATIO By Weight

Tensol 70 Component A	20 parts
Tensol 70 Component B	1 part

It is important that this is done accurately otherwise the cement will not harden properly if different proportions are used.

- Add **Component B** to **Component A** and mix thoroughly by stirring, taking care to entrap as little

air in the adhesive as possible, after mixing cover the vessel and leave to stand for approx. 5 minutes to allow the larger bubbles to rise to the surface.

- The mixed adhesive must be used and the job completed within 20 minutes of adding **Component B**, hardening begins as soon as **Component B** is added to **Component A**, if not used within 20 minutes it will be difficult to use due to thickening of the adhesive and the bond will be weakened.

APPLICATION

- Cementing operations should not be undertaken at temperatures below 15°C otherwise the setting time may be affected. Ideally the room temperature should be 15 - 25 °C.
- The minimum film thickness that can be successfully used is 5 thou (0.13 mm) thick. Since the adhesive shrinks on curing allowance must be made for this when making butt joints and fillet joints. When bonding edge to face the edge should have a 10° chamfer to allow a sufficient quantity of adhesive into the joint.
- Setting begins as soon as **Component B** is added, the cement should harden within 1.5 - 3 hours at 20+/- 5°C, after this time the joint can be handled carefully. Light machining is possible after approx. 4 hours, but a better finish and stronger joint will be obtained if left for 24 hours.
- Once set the cement continues to harden for some time, after several days the bond strength should be adequate for most applications. However the strength of joints can be increased further by heat treatment
 - Do not heat components until at least 1 hour after cement has set.
 - Non thermoformed components - heat for 3 - 4 hours at 80°C.
 - Thermoformed, highly stretched components - heat for 4 - 5 hours at 70°C.
- Gap filling - Because of its low viscosity the gap filling properties of **TENSOL 70** are limited. Special masking techniques will be needed to keep the cement in place if large gaps are to be filled. In addition the cement shrinks in volume by Approx. 20% as it hardens so cavities must be over filled to allow for this.
- Colour - After prolonged outdoor exposure (years) in warm climates a slight yellowing of the bond line may appear. This will not effect the mechanical properties of the cement.
- If **Component B** becomes deeply coloured (yellow/orange) the hardening time should be tested by mixing a small amount of the two components. Obtain a new bottle of **Component B** if the cement is slow to set.

TYPICAL CHARACTERISTICS

	Component A	Component B
Physical Form	Mobile syrup	Liquid
Colour	Slight blue tinge	Pale straw
Chemical Type	Acrylic	Peroxide
Solvent	Methyl Methacrylate	Plasticiser
Viscosity [mPa.s]	Approx. 1500	
Solids Content [%]	100	Approx. 5
Specific gravity	Approx. 1.03	Approx. 1.2
Flammability	Highly flammable	Highly flammable
Cleaner / Thinner	Bostik Cleaner 5	

BSI STANDARDS



FM1696
BS EN ISO 9001:2000



EMS 53282
ISO 14001

PACKAGING

For current pack sizes please contact the Customer Service Department.

STORAGE

Component A - store in the dark in a dry flameproof area between 16 and 20°C.

Component B - store in the dark at 0 - 5°C. At lower temperatures component B may crystallise out of solution. It is important that all solid deposits are re-dissolved before use. This should be done by **carefully** by warming to Approx. 20°C and shaking.

SHELF LIFE

At least 12 months closed in original packaging stored under the above conditions.

Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product connotes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products..

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number on the bottom right hand side of this page.

SMART HELP

Please contact your local representative

