

Einsatzempfehlung

Material	Stahl N/mm ²				Rostfreie Stähle		Guss		NE-Metalle			Superleg.		Stahl gehärtet	
Zugfestigkeit	<500	<800	<1200 (<HRC38)	<1600 (<HRC48)	<800	<1200	GG	GGG	Al Knetleg.	Al SI<10%	Cu,Ms	Ti/Ni/Co <900	900-1500	HRC 48-57	HRC 58-63
8000 424 158 - Vc (m/min)	36	18-36					28-36	23-32	90	55-70	28-70				
Kühlung	Emulsion	Emulsion/Öl					Emulsion	Emulsion	Emulsion	Emulsion	Emulsion/Öl				