RMP

MATERIAL

to 450°C.

Lacquered steel housing.

STANDARD EXECUTION

FEATURES AND APPLICATIONS

Cylindric retaining magnets

(AINiCo) Aluminium-nickel-cobalt magnet, resistant to temperatures up

RMP cylindric retaining magnets are shielded magnetic systems with

For easier handling and for avoiding demagnetisation, these magnets

Red lacquering, resistant to temperatures up to 180°C.

high performances and moderate overall dimensions.

See Guidelines for the choosing (on page 1052).

have an iron plate on their adhesive surface.

threaded hole

RoHS	AN
------	----

RMQ

to 280°C.

STANDARD EXECUTION

FEATURES AND APPLICATIONS

They have a split adhesive surface.

made out of non-magnetic material.

an iron plate on their adhesive surface.

Cylindric retaining magnets

(AINiCo) Aluminium-nickel-cobalt magnet, resistant to temperatures up

RMQ cylindric retaining magnets are unshielded, cast, magnetic systems

To ensure that the adhesive force is not impaired, the fixing screws must be

For easier handling and for avoiding demagnetisation, these magnets have

pass-through hole

Red lacquering, resistant to temperatures up to 180°C.

with high performances and moderate overall dimensions.


See Guidelines for the choosing (on page 1052).




8 6 57 200 8 9 10 10 10 11 12 12 13 13









Code	Description	D	d	L	h	Nominal adhesive forces* [N]	5,2
502701	RMP-AN-12.5	12.5	M4	16	7	20	15
502711	RMP-AN-17	17	M6	16	5	26	29
502721	RMP-AN-21	21	M6	19	7	40	42
502731	RMP-AN-27	27	M6	25	9	65	89
502741	RMP-AN-35	35	M6	30	9	150	190

* The values of the nominal adhesive forces are approximate and refer to magnetic properties observed on laboratory samples.



1074

O

Code	Description	D	d	dmax Ø Screw head	L	h	s	Nominal adhesive forces* [N]	۵۵
502801	RMQ-AN-13	13	4.2	7	10	4.5	2	7	6
502811	RMQ-AN-19	19.1	4.8	8.7	12.7	6.5	5.7	19	23
502821	RMQ-AN-25	25.4	4.5	8.5	20	8	5.6	40	71
502831	RMQ-AN-32	31.8	7.1	10	25.4	12.7	7.9	66	132

* The values of the nominal adhesive forces are approximate and refer to magnetic properties observed on laboratory samples.