# Gap Pad® 3000S30

Thermally Conductive, Reinforced, Soft "S-Class" Gap Filling Material

#### **Features and Benefits**


- Thermal conductivity: 3.0 W/m-K
- Low "S-Class" thermal resistance at very low pressures
- Highly conformable, "S-Class" softness
- Designed for low-stress applications
- Fiberglass reinforced for puncture, shear and tear resistance



Gap Pad 3000S30 is a soft gap filling material rated at a thermal conductivity of 3 W/m-K. The material offers exceptional thermal performance at low pressures due to an allnew 3 W/m-K filler package and low-modulus resin formulation. It is reinforced to enhance material handling, puncture, shear and tear resistance. It is well suited for high performance, low-stress applications that typically use fixed standoff or clip mounting. A conformable yet elastic nature that allows for excellent interfacing and wet-out characteristics, even to rough surfaces and/or topography.

Gap Pad 3000S30 is offered with natural inherent tack on both sides of the material, eliminating the need for thermally-impeding adhesive layers. The material's natural inherent tack allows for stick-in-place characteristics during assembly. Gap Pad 3000S30 is supplied with protective liners on both sides.

Note: Resultant thickness is defined as the final gap thickness of the application.



#### TYPICAL PROPERTIES OF GAP PAD 3000S30 **PROPERTY** IMPERIAL VALUE **METRIC VALUE** TEST METHOD Color Light Blue Light Blue Visual Reinforcement Carrier **Fiberglass** Fiberglass 0.010 to 0.125 0.254 to 3.175 Thickness (inch) / (mm) ASTM D374 Inherent Surface Tack (1- or 2-sided) Density (g/cc) 3.2 32 ASTM D792 Heat Capacity (J/g-K) 1.0 1.0 ASTM E1269 Hardness 40-125 mil (Shore 00) (1) 30 30 ASTM D2240 Young's Modulus (psi) / (kPa) (2) 180 26 ASTM D575 -60 to 200 Continuous Use Temp (°F) / (°C) -76 to 392 **ELECTRICAL** Dielectric Breakdown Voltage (Vac) >3000 >3000 ASTM D149 Dielectric Constant (1000 Hz) ASTM D150 70 70 Volume Resistivity (Ohm-meter) 109 109 ASTM D257 V-O V-O U.L. 94 Flame Rating **THERMAL** Thermal Conductivity (W/m-K) 3.0 3.0 ASTM D5470

- 1) Thirty second delay value Shore 00 hardness scale.
- 2) Young's Modulus, calculated using 0.01 in/min. step rate of strain with a sample size of 0.79 inch². For more information on Gap Pad modulus, refer to Bergquist Application Note #116


#### Typical Applications:

- Processors
- Server S-RAMs
- Mass storage drives
- Wireline/wireless communications hardware
- Notebook computers
- · BGA packages
- Power conversion

## **Configurations Available:**

• Sheet form and die-cut parts available

#### **Building a Part Number**



### **Standard Options**

NA = Selected standard option. If not selecting a standard option, insert company name, drawing number, and revision level

0816 = Standard sheet size 8" x 16", or 00 = custom configuration

02 = Natural tack, both sides

Standard thicknesses available: 0.010", 0.015", 0.020", 0.040", 0.060", 0.080", 0.100", 0.125" GP3000S30 = Gap Pad 3000S30 Material

Note: To build a part number, visit our website at www.bergquistcompany.com.

Gap Pad®: U.S. Patent 5,679,457 and others.



www.bergquistcompany.com

The Bergquist Company -North American Headquarters The Bergquist Company - Europe Bramenberg 9a, 3755 BT Eemnes Netherlands Phone: 31-35-5380684 Fax: 31-35-5380295 18930 West 78th Street Chanhassen, MN 55317 Phone: 800-347-4572 Fax: 952-835-0430

The Bergquist Company - China Rm. 7C, Aihe Mansion No. 629 Ling Ling Road Shanghai, China 200030 Ph: 86-21-6464-2206 Fax: 86-21-6464-2209

All statements, technical information and recommendations herein are based on tests we believe to be reliable, and All statements, lectrical information and recommendations need in a based on reason we delever to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESSED OR IMPLED INCLUDING THE IMPLED WARRANTIES OF MARKETABILITY AND FITNESS FOR PURPOSE. Sellers' and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product. replace sour iglaminy of the product proved to be delective, seeded using user sind determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection therewith. NETHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL, OR CONSEQUENTIAL, INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE A PRODUCT. No statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufactures. PDS 10050 GP 3000S30 0305