

## Product Information

### Double-sided transparent film tape

tesa® 4963 is a transparent double-sided self-adhesive tape, consisting of a PVC-carrier and a rubber adhesive mass system.

tesa® 4963 is largely resistant to plasticizers.

tesa® 4963 is also available in spools with an extended liner acting as "fingerlift" thus allowing easy removal of the liner.

### Main Application

- permanent closure for paper and plastic bags
- self-adhesive mounting of decorative and packaging materials
- splicing of paper, plastic films and metal foils
- fixing of promotion material

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### Technical Data

• Backing material	PVC film	• Type of adhesive	natural rubber
• Color	transparent	• Elongation at break	30 %
• Total thickness	110 µm	• Tensile strength	50 N/cm

#### Adhesion to

• Steel (initial)	5.9 N/cm	• Steel (after 14 days)	6.1 N/cm
• ABS (initial)	5.4 N/cm	• ABS (after 14 days)	6.2 N/cm
• Aluminium (initial)	4.0 N/cm	• Aluminium (after 14 days)	5.2 N/cm
• PC (initial)	6.2 N/cm	• PC (after 14 days)	6.6 N/cm
• PE (initial)	3.8 N/cm	• PE (after 14 days)	4.5 N/cm
• PET (initial)	5.2 N/cm	• PET (after 14 days)	5.4 N/cm
• PP (initial)	4.3 N/cm	• PP (after 14 days)	6.6 N/cm
• PS (initial)	5.3 N/cm	• PS (after 14 days)	6.6 N/cm
• PVC (initial)	5.0 N/cm	• PVC (after 14 days)	5.9 N/cm

#### Properties

• Temperature resistance short term	70 °C	• Resistance to chemicals	●
• Tack	●●●	• Softener resistance	●●
• Ageing resistance (UV)	●	• Static shear resistance at 23°C	●●●●
• Humidity resistance	●●●●	• Static shear resistance at 40°C	●●●

Evaluation across relevant tesa® assortment: ●●●● very good ●●● good ●● medium ● low

#### Additional Information

tesa® 4963 is also available with fingerlift (extended liner) for easy removal of liner.

Liner variants:

- PV0 brown creped PVC film
- PV1 brown glassine paper (71µm)

# tesa® 4963

## Product Information



### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit  
<http://l.tesa.com/?ip=04963>