

Adhesive tapes

Intertape 51595

- ▶ Rare F class insulation laminated tape
UL approved
- ▶ Puncture resistance
- ▶ Excellent dielectric strength
- ▶ 30 % elongation for a conformable ability

		Value	Test norm
Backing		polyester / non woven polyester	
Thermal class	°C	F /155	ASTM-D1000
backing thickness	mm	0.089	ASTM-D1000
Thickness	mm	0.114	ASTM-D1000
Tensile strength	N/25 mm	131	ASTM-D1000
Elongation	%	30	ASTM-D1000
Colour		Natural, black	
Breakdown voltage	V	4500	ASTM-D1000
Insulation resistance	MOhm	10E5	ASTM-D1000
Adhesive		Thermosetting acrylic	
Adhesion to steel	N/25 mm	12.3	ASTM-D1000
UL file #		E20780	
CSA file		LR94980	
Corrosion factor		1.0/A.1	ASTM-D1000
Flammability		BU 2	UL 510

General description

The combination of polyester film and polyester non woven materials can be used on a wide variety of electrical applications. Multi-purpose tape for applications which require a combination tear and puncture resistance, high tensile strength with elongation and excellent dielectric strength.

Application

- Ideal for high volume coil wrapping applications,
- ground and barrier insulation
- Outer protective wrap for bobbin applications,
- Coil end insulation anchoring leads and terminal board pads
- insulation of bus bar' edge when a flexible product is required

Storage Conditions

For the best shelf time storage temperature should be:

15°C to 25°C
relative humidity: 40% +/- 30%

Shelf life

51595 can be stored at room temperature for at least 24 month from date of production



The product properties set forth in this data sheet are based on the results of testing of typical material produced by the affiliated companies of Von Roll Holding Ltd. (underneath referred as Von Roll). Some variation in product properties is typical. Comments or suggestions relating to any subject other than product properties are offered only to call the end-user's or other person's attention to considerations which may be relevant in the independent determination of the use and/or manner of use of product. Von Roll does not claim or warrant that the use of its product will have the results described in this data sheet or that the information provided is complete, accurate or useful. The user should test the product to determine its properties and its suitability for the intended use. Von Roll expressly disclaims any liability for any damage, harm, injury, cost or expense to any person resulting directly or indirectly from that person's reliance on any information contained in this data sheet. Nothing contained in this data sheet constitutes representation or warranty as to any matter whatsoever. Von Roll makes no warranties whatsoever in this data sheet, expressed or implied, including any implied warranty or fitness for a particular use or purpose. Von Roll shall in no event be liable for incidental, exemplary, punitive or consequential damages.