

Einsatzempfehlung

Material	Stahl N/mm ²		Rostfreie Stähle		Guss		NE-Metalle			Superleg.		Stahl gehärtet			
Zugfestigkeit	<500	<800	<1200 (<HRC38)	<1600 (<HRC48)	<800	<1200	GG	GGG	Al Knetleg.	Al Si<10%	Cu, Ms	Ti/Ni/Co <900	900-1500	HRC 48-57	HRC 58-63
40 00 861 005 - Vc (m/min)	15-30	10-25					22-28	18-22		45-55	22-34				
Kühlung	Emulsion	Emulsion					Emulsion	Emulsion		Emulsion	Emulsion/Öl				