

Material

75 FKM 595

auburn

revision index
26

revision date
5/10/2016

page 1 / 3

Physical properties

| | nominal range | typical values | |
|---|----------------|----------------|-------------------|
| Density DIN EN ISO 1183-1 | 2.00 ±0.03 | 2.00 | g/cm ³ |
| Hardness DIN ISO 7619-1 | 75 ±5 | 75 | Shore |
| Rebound resilience DIN 53512 | > 3 | 6 | % |
| Modulus 100 %, DIN 53504, S2 | > 3.5 | 5.9 | MPa |
| Tensile strength DIN 53504, S2 | > 7.5 | 9.8 | MPa |
| Elongation at break DIN 53504, S2 | > 200 | 278 | % |
| Compression set DIN ISO 815, 22 h, 175 °C | < 45 | 33 | % |
| Tear strength DIN 53515 | > 8 | 12.5 | KN/m |
| Low Temperature DIN 53765, DSC | --- | -18 | °C |
| Temperature range | -30°C to 200°C | | |

Declarations of conformity

| | Country | Part | Remark | Expires | unlimited |
|----------|---------|------|--|---------|-------------------------------------|
| ADI Free | | | | | <input checked="" type="checkbox"/> |
| RoHS | | | Restricted substances in electrical and electronic equipment | | <input checked="" type="checkbox"/> |

Freudenberg

Freudenberg Sealing Technologies
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com



Material

75 FKM 595

auburn

revision index
26

revision date
5/10/2016

page 2 / 3

Tested after ASTM D 2000: M 2 HK 707 B37 B38 EF31 EO78 Z1 Z2 Z3 Z4

| | | nominal range | typical values |
|--|-------|----------------------|-----------------------|
| Hardness | Shore | 70 ±5 | 75 |
| Tensile strength | MPa | min. 7 | 10.1 |
| Elongation at break | % | min. 175 | 272 |
| B37 Compression set 22h/175°C | % | 50 | 25 |
| B38 Compression set 22h/200°C | % | 50 | 38 |
| EF31 Change after aging in Fuel C 70h/23°C | | | |
| Hardness | Shore | ±5 | -2 |
| Tensile strength | % | -25 | -14 |
| Elongation at break | % | -20 | -10 |
| Volume | % | 0 to 10 | 3.5 |
| EO78 Change after aging in Fluid No. 101 70h/200°C | | | |
| Hardness | Shore | -15 to 5 | -7 |
| Tensile strength | % | -40 | -22 |
| Elongation at break | % | -20 | -15 |
| Volume | % | 0 to 15 | 13.2 |
| Z1 Hardness DIN 53505, Shore A, 23 °C | Shore | 75 ±5 | 75 |
| Z2 Low Temperature DIN 3761 Teil 15, DSC | °C | --- | -18 |
| Z3 Low-temperature resistance (F13) ASTM D2137, Method A, 3 min/-10°C | | pass | pass |
| Z4 Change after aging in Air 70h/250°C | | | |
| Hardness DIN ISO 7619-1, Shore A, 23 °C | Shore | --- | 10 |
| Tensile strength DIN 53504, S2, 23 °C | % | --- | 25 |
| Elongation at break DIN 53504, S2, 23 °C | % | --- | -45 |

Freudenberg

Freudenberg Sealing Technologies
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com



Material 75 FKM 595

auburn

revision index

26

revision date

5/10/2016

page

3 / 3

Temperature-range: - 30 °C to +200 °C (Depending on the specific applikations and lubricants)
Max. permanent temperature in gear oil: + 150 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg Sealing Technologies
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

