

# tesa® ACX<sup>plus</sup> 7063



## Product Information

### ACX<sup>plus</sup> High Adhesion 800µm

tesa® ACX<sup>plus</sup> 7063 is a black acrylic foam tape.

It consists of a high-performance acrylic system and is primarily characterised by its bonding power, stress dissipation and its temperature and weather resistance.

Due to its unique formulation it combines a very high adhesion level with a very good resistance against plasticizer migration. It is especially designed for the bonding of “hard-to-bond-materials” such as powder coatings or plastic materials. Even for combinations of such materials with all kind of metals, or metal/metal bonding, it offers a convenient solution due to high process safety.

The visco-elastic, foamed acrylic core compensates different thermal elongation of bonded parts.

The product provides a very high immediate tack and peel adhesion. tesa® ACX<sup>plus</sup> 7063 is a black acrylic foam tape. It consists of a high-performance acrylic system and is primarily characterised by its bonding power, stress dissipation and its temperature and weather resistance.

Due to its unique formulation it combines a very high adhesion level with a very good resistance against plasticizer migration. It is especially designed for the bonding of “hard-to-bond-materials” such as powder coatings or plastic materials. Even for combinations of such materials with all kind of metals, or metal/metal bonding, it offers a convenient solution due to high process safety.

The visco-elastic, foamed acrylic core compensates different thermal elongation of bonded parts.

The product provides a very high immediate tack and peel adhesion.

## Main Application

Bonding of hard-to-bond materials such as

- Bumper rails
- Powder coated blades and panels
- Air distributaries

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Technical Data

• Backing material	foamed acrylic	• Type of adhesive	tackified acrylic
• Colour	deep black	• Elongation at break	600 %
• Total thickness	800 µm		

### Adhesion to

• Steel (after 3 days)	30.0 N/cm	• Glass (after 3 days)	32.0 N/cm
• Aluminium (after 3 days)	32.0 N/cm	• PMMA (after 3 days)	27.0 N/cm

# tesa® ACX<sup>plus</sup> 7063



## Product Information

### Properties

• Temperature resistance short term	170 °C	• Resistance to chemicals	●●●●
• Temperature resistance long term	70 °C	• Softener resistance	●●●●
• Tack	●●●●	• Static shear resistance at 23°C	●●●●
• Ageing resistance (UV)	●●●●	• Static shear resistance at 70°C	●●
• Humidity resistance	●●●●	• T-block	●●●●

Evaluation across relevant tesa® assortment: ●●●● very good ●●● good ●● medium ● low

### Additional Information

PV 22 = White PE coated paper liner tesa® ACX<sup>plus</sup> branded

PV 24 = Blue filmic liner

Adhesion values to PMMA, glass and aluminum are not part of the product specification.

tesa® ACX<sup>plus</sup> 7063 is recognised according to UL Standard 746C. UL File QOQW2.E309290

## Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit  
<http://l.tesa.com/?ip=07063>