


# Liquidtight Flexible Shielding Conduit

# TYPE - HFEMCS



				Carton	Footage
Trade Size	Туре	Inside Bend Radius	Wt. (Lbs.)/ 100 Ft.	Length	Part #
3/8"	HFEMCS-10	3.0"	27	50	86007
1/2"	HFEMCS-11	3.0"	35	50	86107
3/4"	HFEMCS-12	4.0"	43	50	86207
1"	HFEMCS-13	4.0"	85	50	86307
1-1/4"	HFEMCS-14	4.5"	101	50	86402
1-1/2"	HFEMCS-15	7.0"	140	50	86502
2"	HFEMCS-16	9.5"	180	50	86602





# **COMBUSTION & FLAMMABILITY PROPERTIES**

*Combustion & Flammability Properties:	Test	Value	
Vertical Burn (Material)	UL94	V-0 Rating No Flaming Drips	
Vertical Burn (Conduit)	UL360	Pass No Flaming Drips	
Oxygen Index %	D2863	28.5	
Flame Spread Index	ASTM E162	20; No Flaming Drips	
Flame Propagation	ASTM C542 (NFPA-130)	Pass No Flaming Drips	
Smoke Generation (Flaming)	ASTM E662 (NFPA 258)	Ds 50@1.5 Min/ Ds 102@4.0 Min	
Smoke Generation (Non-Flaming)	ASTM E662 (NFPA258)	Ds 5@1.5 Min/ Ds 26@4.0 Min	
Toxic Gas Generation	BOMBARDIER SMP 800-C	Pass	
Toxicity Index	NES 713	3.9	

\* Test data is based on controlled laboratory conditions and does not necessarily reflect performance in actual fire conditions. Additional product information available upon request.

See Chart for Dimensions and Tolerances.

#### **TYPE - HFEMCS**

Type HFEMCS<sup>TM</sup> is a hybrid of HFSLA<sup>TM</sup> and HFEMS<sup>TM</sup>. It uilizes the same bronze core and Polyurethane jacket as HFEMS<sup>TM</sup>, but gets further screening protection from a tinned copper braid as found in the HFSLA<sup>TM</sup> product.

,br>Type HFEMCS™ liquidtight flexible shielding conduit is designed for field installations where safety concerns exist regarding a material's reaction in a fire situation. The specially formulated thermoplastic polyurethane jacket has excellent flame retardancy and low smoke characteristics. Acidic gases such as hydrogen chloride, hydrogen fluoride and hydrogen bromide are virtually eliminated as products of combustion.

### **Tests Include:**

WEEE and RoHS Compliant

## STANDARD COLORS:

Gray and Black. Other colors and jacketing materials available upon request

For UL and CSA version, consult factory

## **WORKING TEMPERATURES:**

-40°C to 80°C

Flexibility: See the Flexibility Comparison Guide

**Metal Used: Bronze** 

Plastic Used: PU See the Chemical Resistance Guide

Strenath	Direct	Halogen Free		Accepts Standard Liquidtight Fittings	Self Extinquish	EMI/RFI Shielding	Oil Resistance	Acid Resistance
		X	X	X	X	X	X	X