# productinformation

# tesa® 62936

## Double-sided PE foam mounting tape

tesa® 62936 is a double-sided PE-foam tape for constructive mounting applications. It consists of a highly conformable PE-foam backing with a tackified acrylic adhesive.

#### Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- High ultimate adhesion level for a secure bonding performance
- UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorbtion

## Main Application

- Interior wall cladding panels
- Bumper rails on commercial freezers
- Injection moulded plastic parts
- Mirrors and coloured glass panels

#### Technical Data

	Backing material	PE foam		Type of adhesive	tackified acrylic
	Color	black/white	•	Elongation at break	175 %
٠	Total thickness	1600 μm	•	Tensile strength	9 N/cm

#### Adhesion to

•	Steel (initial)	16.0 N/cm	•	Steel (after 14 days)	19.0 N/cm
•	ABS (initial)	17.0 N/cm		ABS (after 14 days)	19.0 N/cm
•	Aluminium (initial)	15.0 N/cm		Aluminium (after 14 days)	19.0 N/cm
•	PC (initial)	19.0 N/cm		PC (after 14 days)	19.0 N/cm
•	PE (initial)	2.0 N/cm		PE (after 14 days)	3.0 N/cm
•	PET (initial)	15.0 N/cm		PET (after 14 days)	19.0 N/cm
•	PP (initial)	3.0 N/cm		PP (after 14 days)	7.0 N/cm
•	PS (initial)	19.0 N/cm		PS (after 14 days)	19.0 N/cm
•	PVC (initial)	19.0 N/cm		PVC (after 14 days)	19.0 N/cm

For latest information on this product please visit <a href="http://l.tesa.com/?ip=62936">http://l.tesa.com/?ip=62936</a>

# tesa® 62936

# Double-sided PE foam mounting tape

## **Properties**

- Temperature resistance short termTemperature resistance long term
- Tack
- Iack
- Ageing resistance (UV)
- Humidity resistance

- Resistance to chemicals
  - Softener resistance
  - Static shear resistance at 23°C
  - Static shear resistance at 40°C

medium

low





Evaluation across relevant tesa® assortment: • • • • very good • • • good

80°C

80°C

### Additional Information

Liner variants:

PV0 brown glassine paper (71  $\mu m$ )

PV14 white PE-coated paper (120 μm)

PV10 red filmic liner (120 µm)

tesa® 62936 has been tested by TÜV Rheinland, Germany. The test confirms the longterm adhesion performance after IEC 61215 / 61646 climate tests and a 85°C temperature resistance. (TÜV report number 21209595).

#### Peel Adhesion:

- immediate: foam splitting on PC, PS, PVC
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC